

ACRIFIX® 1S 0116

1-Component Solvent Adhesive

Product and Use

Type

1-Component solvent adhesive.
Viscous, clear, colorless to slightly yellowish, physically curing.

Applications

For making T-bonds and bonding narrow areas of all kinds of uncrosslinked PLEXIGLAS®, but also for other plastics such as PS, SBC, ABS, PVCu, CAB. ACRIFIX® 1S 0116 is only slightly gap-filling. The bond is firm within a short time. Rapid further treatment possible. High ultimate strength. For use with other products, conduct prior tests.

Storage/Transport

Keep container tightly closed in a cool place.
UN 1133

Working Instructions

Normally, a sawn or milled edge of one article is bonded at right angles to the original surface of another. In areas where a high stress level is to be expected, avoid bonding or anneal the parts beforehand to relieve stress. The parts to be bonded must have a very accurate fit. Grooves and notches become only partially filled. Clean the adherents with petroleum ether or isopropyl alcohol before applying the adhesive.

ACRIFIX® 1S 0116 is applied from the tube or a nozzled bottle to the edge of one of the items to be bonded, which, starting from one side, is then placed in contact with the second. After a short holding time, the bond is locked in position. When bonding sawn edges, bubble formation can be

reduced by passing the edges over with a scraper or smoothing them with fine, wet abrasive paper (grit 400 to 600 – if possible at right angles to the sheet edge), by milling or diamond cutting before the actual bonding process is started. Slight pressure applied to the bonded surface during drying can also reduce bubble formation.

Note

Whitening around the adhesive joint is due to water condensing from the air (especially if the room temperature is low).

Attention: When pre-bonding with ACRIFIX® 1S 0116, curing of ACRIFIX®2R adhesives can be impaired.

ACRIFIX®1S 0116 can turn yellow as a result of exposure to light, however the yellowing has no effect on the adhesion.

For further details please see our Guideline, "Joining Ref. No.: 311-3"

Properties of Bonds

Initial bond:

PLEXIGLAS® GS/PLEXIGLAS® GS: ~ 60 to 90 sec
PLEXIGLAS® XT/PLEXIGLAS® XT: ~ 30 to 50 sec

Subsequent treatment of bonded items:
not within the first three hours

Tensile shear strength ($v = 5 \text{ mm/min}$; butt joints, free from bubbles):

Annealing increases the strength and also improves the weather resistance.

PLEXIGLAS® GS 233/0F00:

28 ± 5 MPa (non-annealed),

37 ± 5 MPa (annealed for 5 hrs at 80 °C)

PLEXIGLAS® XT 20070/0A000:
30 ± 5 MPa (non-annealed),
37 ± 5 MPa (annealed for 5 hrs at 80 °C)

Appearance:

Colorless, clear.
Rather more bubbles with PLEXIGLAS® XT and fewer with PLEXIGLAS® GS. Bleeding may occur with colored parts to be bonded.

Limitation of Liability

Our ACRIFIX® adhesives and other service products were developed exclusively for use with our PLEXIGLAS® products and are specially adjusted to the properties of these materials. Any recommendations and guidelines for workshop practice therefore refer exclusively to these products.

Claims for damages, especially under product liability laws, are ruled out if made in connection with the use of products from other manufacturers.

For further information on safety measures, the exclusion of health risks when handling adhesives and on their disposal, see our Safety Data Sheet.

Availability according to the current sales range.

Safety Measures and Health Protection

Labeling according to Regulation (EC) 1272/2008

Danger, contains ethylformate, nitroethane, butan-1-ol.



Harmful if swallowed. (H302)
Highly flammable liquid and vapour. (H225)
Causes serious eye irritation. (H319)
Harmful if inhaled. (H332)
May cause respiratory irritation. (H335).
Wear protective gloves/protective clothing/eye protection/face protection. (P280)
Call a POISON CENTER or doctor/physician if you feel unwell. (P312)

IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. (P304+P340)

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. (P305+P351+P338)
Dispose of contents according to local disposal regulations. (P501)

Typical Values

Properties	Values
Viscosity; Brookfield II/12/20 °C:	650 to 900 mPa · s
Density (20 °C):	~ 1.0 g/cm3
Refractive index n _D ²⁰ :	~ 1.39
Color:	clear to yellowish; color does not affect bonding properties
Flash point (DIN 53213):	< 4 °C
Solids content:	approx. 10 %
Storage stability:	2 years after filling, if correctly stored
Storage temperature:	max. 30° C
Packaging materials:	glass and aluminum bottles(coated inside)
Thinner:	ACRIFIX® 1S 0116 can be thinned with ACRIFIX® 1S 0117 at any ratio
Cleaning agents for equipment:	Ethyl acetate
Curing:	physically, through evaporation and absorption in the bonded articles.

® = registered trademark PLEXIGLAS and ACRIFIX are registered trademarks of Evonik Röhm GmbH, Darmstadt, Germany. Evonik Röhm GmbH is certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment).

Evonik is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, also with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Performance Materials GmbH

Acrylic Polymers

Kirschenallee, 64293 Darmstadt, Germany

info@plexiglas.net www.plexiglas.net www.evonik.com

Ref.-No. 391-21 August 2015